

IN THE SPECIFICATION

Page 6, second line from the top of the page, please correct:

a! magnesium and/or aluminum silicates. Preferred of this group are thixotropic minigels, e.g. Mg silicate, e.g. ~~MinuGel G-35 and Minugel AR~~ **MINUGEL™ G-35 and MINUGEL™ AR**. Attapulgite and montmorillonite clays, as well as mixtures of the above, are also suitably employed as component (d) in the present composition.

Page 9, in the Table please correct:

ar

	<u>COMPONENT</u>	<u>Wt. %</u>
1.	100% non-blown asphalt at about 420 F.	63.94
2.	50/50 % mixture of naphtha/xylene	18.46
	Kwik-Dri 66* <u>(KWIK DRI™ 66)*</u>	4.5
	Mineral Spirits	2.1
3.	Isodecyloxy mine <u>amino acetate (Pa-14) (PA-14)</u>	0.5
4.	Magnesium silicate (Minugel 35) <u>(MINUGEL™ 35)</u>	6.5
5.	Cellulose fiber	2.0

* Stoddard solvent